

**Corrosion resistant primer red-brown, inert pigmented,  
based on Setal A F 26 X**

## Formulation

Raw Material	Supplier	% by wt.
Setal A F 26 X	(1)	35.2
Methoxy propanol		2.7
Micro-Talc IT extra	(2)	10.6
Bayferrox 140	(6)	4.2
Bayferrox 420	(6)	4.2
Omya BLP 3	(3)	14.8
Calcit GS 20	(4)	8.4
<b>Borchi® Set 134</b>	(5)	2.6
White spirit D 60		16.3
<b>Octa-Soligen® 203</b>	(5)	0.2
<b>Borchi® Nox M2</b>	(5)	0.8
<i>Total</i>		<i>100.0</i>

## Suppliers

- (1) Nuplex ([www.nuplex.com](http://www.nuplex.com))
- (2) Luzenac ([www.imerystalc.com](http://www.imerystalc.com))
- (3) Omya ([www.omya.com](http://www.omya.com))
- (4) Calcitwerk Schön & Hippelein ([www.calcitsh.de](http://www.calcitsh.de))
- (5) Borchers ([www.borchers.com](http://www.borchers.com))
- (6) Lanxess ([www.bayferrox.com](http://www.bayferrox.com))

Updated: 25.01.2016

**Borchers GmbH**

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666  
Fax: +49 (0) 2173 – 39 26 999 / Internet: [www.borchers.com](http://www.borchers.com) / E-Mail: [info.info@borchers.com](mailto:info.info@borchers.com)

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.