

Glossy two-pack PU clear coat, fast drying, for spray application, based on Setalux D A 450 BA/X and Desmodur N 75

	Raw Material	Supplier	% by wt.
Component 1	Setalux D A 450 BA/X	(4)	54.0
	Butylacetat		14.0
	Borchi® Gol LAC 80, 50% in xylene / butylacetat / methoxy propyl acetate (1:1:1)	(2)	0.3
	CAB 381-2, 25% in butyl acetate	(3)	12.0
	Methyl ethyl ketone		19.7
	<i>Total</i>		<i>100.0</i>
	<i>Homogenizate in a dissolver</i>		
Component 2	Desmodur N 75, 75% in xylene / methoxy propyl acetate	(1)	8.0

Data		
Comp.1 : Comp. 2 – Mixing ratio		100 : 8
Solids content (Comp. 1), DIN EN ISO 3251		30 %
Solids content on application		30.5 %
Thinning for spray viscosity: xylene / butyl acetate (1:1)		10 %
Spray viscosity, DIN 53211-cup 4 mm, at 23 °C		ap. 24 s
Pot life		> 8 h
Drying TG 1 (sand dry), DIN 53150, at 23 °C		5 min
Hardness (König method), DIN EN ISO 1522 - after 1week		ap. 195 s
Gloss Gardner (20°/ 60° angle), DIN 67530 / ISO 2813		80 / 86
Haze		13
Chemical resistance, DIN 68861 part 1B (tested on beech wood veneered)		resistant

Suppliers

- (1) Covestro (www.covestro.com)
- (2) Borchers (www.borchers.com)
- (3) Eastman Chemical (www.eastman.com)
- (4) Nuplex (www.nuplex.com)

Updated: 25.01.2016

Borchers GmbH

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666
 Fax: +49 (0) 2173 – 39 26 999 / Internet: www.borchers.com / E-Mail: info.info@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.