

Aqueous pigment concentrates, binder free

Pigment paste	A	B	C
Colour index	P.R. 122	P.Y. 74	P.B. 15:2
Pigment Trade name (1)	Sunfast red 228-0641	Sunbrite Yellow 272-4608	Sunfast blue 248-615
Pigment	35	40	35
Borchi® Gen 0851 (2)	28	16	28
Water	36	43	36
Borchers® AF T (2)	1	1	1
Total	100	100	100
Dosage of additive active content based on pigment content	40 %	20 %	40 %

All indications are as supply form (in % by wt).

Dispersion: 60 min, on Skandex BAS-20, with 150 g Zr-Silicate grinding beads (2mm)

Data

Particle size (using Grindometer)	< 6 µm	< 6 µm	< 7 µm
Viscosity (at shear rate 100 s ⁻¹ ; 23 °C)	1250 mPa·s	280 mPa·s	280 mPa·s
Storage (2 weeks at 50 °C)	no significant alteration of the viscosity and particle size		

Suppliers (1) Sun Chemical (www.sunchemical.com)
(2) Borchers (www.borchers.com)

Updated: 25.01.2016

Borchers GmbH
Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666
Fax: +49 (0) 2173 – 39 26 999 / Internet: www.borchers.com / E-Mail: info.info@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.