

Latex paint for indoor and outdoor use, based on Acronal LR 9014

	Raw Material	Supplier	% by wt.
Pigment paste formulation	Water		6.5
	Dispersion agent		1.2
	Kronos 2360	(1)	25.4
	Borchers® AF 0670	(2)	0.3
	<i>Total</i>		33.4
	<i>Dispersion: about 30 min. at 3000 rpm</i>		
Let down	Acronal LR 9014	(3)	61.9
	Plastilit 3060	(3)	2.0
	Water		2.8
	Borchers® AF 0670	(2)	0.2
	Borchi® Gel 0434	(2)	1.5
	<i>Total</i>		100.0

	Method	Result	
Technical Data	Krebs-Stormer viscosity	200 rpm	95 KU
	ICI viscosity	10000 1/s	1.0 – 1.3
	Gloss	60°	55

Suppliers

- (1) Kronos Titan (www.kronostio2.com)
- (2) Borchers (www.borchers.com)
- (3) BASF (www.basf.com)

Updated: 25.01.2016

Borchers GmbH

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666
 Fax: +49 (0) 2173 – 39 26 999 / Internet: www.borchers.com / E-Mail: info.info@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.