

Aqueous black pigment concentrates, binder free

Pigment paste (Supplier)	A	B	C	D	E
Colour index	P.BL 7				
Pigment Trade name (1)	Special Black 4	Printex U	Printex 45	Printex 55	Carbon black FW 200
Pigment	24.50	24.50	29.69	26.49	13.07
Borchi® Gen 0851 (2)	17.15	17.15	11.88	15.89	20.90
Water	56.35	56.35	56.43	55.62	64.03
Borchers® AF T (2)	2.00	2.00	2.00	2.00	2.00
<i>Total</i>	<i>100.00</i>	<i>100.00</i>	<i>100.00</i>	<i>100.00</i>	<i>100.00</i>
Dosage of additive active content based on pigment content	35 %	35 %	20 %	30 %	80 %

All indications are as supply form (in % by wt).

Dispersion: 60 min, on Skandex BAS-20, with 150 g Zr-Silicate grinding beads (2mm)

Data

Particle size (using Grindometer)	< 3 µm	< 5 µm	< 7 µm	< 5 µm	< 6 µm
Viscosity (at shear rate 100 s ⁻¹ ; at 23 °C)	50 mPa·s	80 mPa·s	38 mPa·s	36 mPa·s	90 mPa·s
Storage (2 weeks at 50 °C)	no significant alteration of the viscosity and particle size				

Suppliers (1) Orion Engineered Carbons (www.orioncarbons.com)
 (2) Borchers Americas (www.omgi.com)

Updated 26.01.2016

Borchers Americas, Inc.
 811 Sharon Drive / Westlake, OH 44145 / Telephone: 440.899.2950 800.321.9696
 Fax: 440.808.7117 / Internet: www.borchers.com / E-Mail: info.us@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.