

## 12 % Cobalt Catalyst 510

Promoter for unsaturated polyester resins

### Physical Characteristics

Metal content	Co: 11.90 - 12.10 %
Non-volatile content	65.00 - 75.00 % ASTM D 1644
Viscosity	A-5 to I ASTM D 2373
Specific gravity	1.000 - 1.050 (25°C) ASTM D 1963
Density	NA

### Features

- Cobalt salt of 2-ethylhexanoic acid
- Imparts less color
- Decomposes the peroxide initiator which then forms the free radicals needed to begin polymerization

### Applications

- Solvent-based unsaturated polyester
- Vinyl ester

### Dosage

NA

### Storage

Keep containers tightly closed in a dry, cool and well-ventilated place. Keep away from sources of ignition. Store in original container. Store in accordance with local regulations. Keep away from food, drink and animal feed stuffs. Keep at temperatures between 5 °C and 30 °C.

### Safety

Please refer to our safety data sheet for information relating to product safety.

---

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: [www.borchers.com](http://www.borchers.com) / E-Mail: [info.us@borchers.com](mailto:info.us@borchers.com)

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

Edition: 08/2021

