

15 % Potassium Hex-Cem[®] Water White

Potassium Octoate Synergist with Cobalt for Gel Coats and UPR Systems

Physical Characteristics

Metal content	K: 14.90 - 15.20 %
Non-volatile content	>= 85.0 % D1644
Viscosity	A-5 to Z-1 ASTM D 2373
Specific gravity	1.070 - 1.150 (25°C) ASTM D 1963
Density	NA

Features

- Potassium salt of 2-ethylhexanoic acid in mineral spirits
- Has a higher rate of catalytic activity than many other promoters
- Enables the resin formulator to reduce the amount of cobalt required thereby obtaining a lighter colored product
- Interacts positively within the system to maintain reactive cobalt levels and reduce gel-time drift

Applications

- Applications where color is desired
 - Castings
 - Marble
 - Gel coat

Dosage

NA

Storage

Keep containers tightly closed in a dry, cool and well-ventilated place. Keep away from sources of ignition. Store in original container. Store in accordance with local regulations. Keep away from food, drink and animal feed stuffs. Keep at temperatures between 5 °C and 30 °C.

Safety

Please refer to our safety data sheet for information relating to product safety.

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: www.borchers.com / E-Mail: info.us@borchers.com

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.