

8 % Copper Nap-All®

Catalyst / Enhancer

Physical Characteristics

Metal content	Cu: 7.90 - 8.20 %
Non-volatile content	<= 85.0 % ASTM D 1644 B
Viscosity	A-5 to Z ASTM D 2373
Specific gravity	0.984 - 1.032 (25°C) ASTM D 1963
Density	NA

Features

- Copper salt of naphthenic acid in mineral spirits
- Controls exotherm to reduce surface cracks and add shelf stability to polyester resins
- Can be used in both the synthesis of the unsaturated polyester resin and in the final resin formulation
- At concentrations of 0.01% it reduces surface cracks and irregularities that may develop in large polyester casting

Applications

- Promoted and unpromoted resins

Dosage

NA

Storage

Keep containers tightly closed in a dry, cool and well-ventilated place. Keep away from sources of ignition. Store in original container. Store in accordance with local regulations. Keep away from food, drink and animal feed stuffs. Keep at temperatures between 5 °C and 30 °C.

Safety

Please refer to our safety data sheet for information relating to product safety.

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: www.borchers.com / E-Mail: info.us@borchers.com

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.