

## Borchers® LH 10

Catalyst (DBTL) for water-based two-component PU coatings

### Physical Characteristics

Metal content	NA
Non-volatile content	NA
Viscosity	NA
Specific gravity	NA
Density	1.01 g/cm <sup>3</sup> (20°C)

### Features

- Accelerates cross-linking process
- Improves the drying of chemically curing systems
- Enhances scratch resistance, hardness and mechanical persistence

### Applications

- Coatings
  - Aqueous two-component polyurethane
  - High gloss

### Dosage

Borchers® LH 10 has to be added to the grinding process of the base component. The recommended amount should be around 0.4 - 0.6 % regarding solid content of the binder. The precise dosage should be determined beforehand in trials.

### Storage

Protect from the effects of weathering and store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product. It has to be protected against frost.

### Safety

Please refer to our safety data sheet for information relating to product safety.