

Octa-Soligen® Zirconium 10 aqua

Zirconium drier

Physical Characteristics

Appearance	Clear, low-viscous, colorless to yellowish liquid
Metal content	Zr: 9.80 - 10.20 % ISO 4619
Non-volatile content	NA
Viscosity	Max. 150 mPa.s (20°C) ISO 3219 (A)
Specific gravity	NA
Density	1.000 - 1.050 g/cm ³ DIN 51757 (20 °C)
Solvent	Water dispersible oil

Features

- Widely used secondary drier with cobalt, manganese and calcium
- Based on metal salts of 2-ethylhexanoic acid (octoates) or their isomers
- Promotes through-drying primarily by the formation of coordination bonds
- Better properties in terms of color, yellowing and stability compared to other secondary driers

Applications

- Water-based systems

Dosage

In our experience, the percentage addition of zirconium, calculated on the metal content per solid binder, is approx. 0.05 - 0.30 %. The exact amount required depends on the binder used and should always be determined in preliminary trials.

Storage

Protect from the effects of weathering and store at temperatures between 5 and 30 °C. Once opened, containers should be resealed immediately after each removal of the product.

Safety

Please refer to our safety data sheet for information relating to product safety.

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: www.borchers.com / E-Mail: info.us@borchers.com

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.