

Poly-Cure® 503

Accelerator for Gel Coats and UPR Systems

Physical Characteristics

Metal content	Co: 2.90 - 3.10 % K: 8.40 - 8.60 %
Non-volatile content	65 - 77 % ASTM D 1644
Viscosity	A-5 to Z ASTM D 2373
Specific gravity	1.01 - 1.06 (25° C) ASTM D 1963
Density	NA

Features

- Blend of metal salts of 2-ethylhexanoic acid in mineral spirits
- Designed as an alternative to cobalt promoters as a polyester accelerator
- Higher catalytic activity than many other promoters
- Contributes to a reduction in gel-time drift

Applications

- Coatings
 - o Castings
 - o Marble
 - Gel

Dosage

NA

Storage

Keep containers tightly closed in a dry, cool and well-ventilated place. Keep away from sources of ignition. Store in original container. Store in accordance with local regulations. Keep away from food, drink and animal feed stuffs. Keep at temperatures between 5 °C and 30 °C.

Safety

Please refer to our safety data sheet for information relating to product safety.

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: www.borchers.com / E-Mail: info.us@borchers.com

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

Edition: 08/2021

Milliken