


Borchi® Gen 0851 with Orion FW310

EXCELLENT JETNESS IN WATER BASED SYSTEMS




Jetness (My) and Hue Dependent Blackness (Mc)
2K WB system



	Borchi® Gen 0851	Ref 1	Ref 2
My	303	289	285
Mc	315	289	288


Darkness L* and Undertone (b*)



	Borchi® Gen 0851	Ref 1	Ref 2
L*	0.84	1.16	1.28
b*	-0.44	-0.03	-0.19

- Best jetness and blackness
- Best bluish undertone
- Better pigment wetting

Jetness (My) and Hue Dependent Blackness (Mc)
OEM WB system




3% pigment letdown in OEM WB Clear coated system

2K WB Clear

Resin Free Pigment Concentrate	1	2	3
Water	54.00	41.14	46.50
Borchi® Gen 0851 (50% active)	30.00		
Reference 1 (35% active)		42.86	
Reference 2 (40% active)			37.50
Borchers® AF 1171	0.50	0.50	0.50
AMP 95	0.50	0.50	0.50
Orion FW 310	15.00	15.00	15.00
Total	100.00	100.00	100.00
%DOP	100	100	100

3% pigment letdown in 2K WB Clear system
Grinding media Zr 0.8 mm / Grinding time: Lau 2h



Order your sample at:

www.borchers.com

1 (800) 321-9696 ■ cust.service.us@borchers.com


Borchi® Gen 0451 with Orion FW310

EXCELLENT JETNESS IN SOLVENT BASED SYSTEMS




- Best jetness and blackness
- Best bluish undertone
- Better pigment wetting
- Highest gloss performance

L* & b* 2KPU SB Coating



Jetness 2KPU SB Coating




Resin Free Pigment Concentrate

Butyl Acetate	80.00
Borchi® Gen 0451 (100% active)	10.00
Orion FW 310	10.00
Total	100.00
%DOP	100

3% pigment letdown in 2KPU SB system
Grinding media Zr 0.8 mm / Grinding time: Lau 2h

20° & 60° Gloss



Order your sample at:

www.borchers.com

1 (800) 321-9696 ■ cust.service.us@borchers.com