

White and yellow, glossy two-pack PU topcoat,
based on Desmophen 651 / Desmodur N 75

		A white	B yellow	
	Raw Material	Supplier	% by wt.	
Comp. 1	Desmophen 651, 67% in xylene / methoxy propyl acetate	(1)	24.00	24.00
	Borchi® Gen 1051	(2)	1.10	1.70
	Bentone 38 – Paste*		2.00	2.00
	Kronos 2310	(3)	20.00	—
	Sachtleben R-KB-4	(4)	—	16.00
	Bayfast Yellow Y 5688	(5)	—	1.50
	Fanchon Fast Yellow Y 5740	(6)	—	1.50
	Borchi® Gol OL 17, 50% in xylene / butyl acetate / methoxy propyl acetate (1:1:1)	(2)	0.30	0.30
	Solvent-mixture**		18.50	18.90
	Tinuvin 292, 50% in xylene / butyl acetate / methoxy propyl acetate (1:1:1)	(7)	0.60	0.60
	Borchi® Kat 0245	(2)	0.20	0.20
	Total		66.70	66.70
<i>Dispersion: 1h mit Skandex - Zr-silicate grinding beads (2 mm)</i>				
Comp. 2	Desmodur N 75, 75% in xylene / methoxy propyl acetate	(1)	19.75	19.75
	Additive TI	(2)	0.30	0.30
	Solvesso 100 / Methoxy propyl acetate (1:1)		13.25	13.25
	Total		33.30	33.30
	Total: Comp. 1+2		100.00	100.00

** Methoxy propyl acetate / Solvesso 100 / Butyl acetate / Butoxyl (55:10:25:10)

*Bentone Paste Formulation	Bentone 38	(8)	10.0
	Borchi® Gen TS	(2)	5.0
	Solvesso 100		85.0
	Total		100.0

Application	Compressed-air spraying	2 - 3 bar pressure
	Adjust for spray viscosity after mixing the components.	

Data	A	B
	white	yellow
Mixing ratio Comp. 1:2	2 : 1	2 : 1
Solids content	ap. 52 %	ap. 52 %
Binder content	ap. 31 %	ap. 31 %
Spray viscosity, DIN 53211-cup 4mm, at 23 °C	20 s	20 s
Pot life, DIN 53150-cup 4mm , at 23 °C	ap. 7 h	ap. 7 h
Drying, DIN 53150 TG1 (sand dry) -100 µm wet film thickness on glass	ap. 1 h	ap. 1 h
Hardness (König method) - after 1 day (in s) DIN EN ISO 1522 -100µm wet film thickness on glass	ap. 197	ap. 197
Haze and Gloss (20°/ 60° angle) DIN 67530 / ISO 2813	18 / 88 / 94	14 / 90 / 95

Suppliers

- (1) Covestro (www.covestro.com)
- (2) Borchers (www.borchers.com)
- (3) Kronos Titan (www.kronostio2.com)
- (4) Venator (www.venatorcorp.com)
- (5) Lanxess (www.lanxess.com)
- (6) Sun Chemical Pigments (www.sunpigments.com)
- (7) Ciba Speciality Chemicals (www.cibasc.com)
- (8) Elementis (www.elementis.com)

Updated: 16.04.2020

Borchers GmbH

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666
Fax: +49 (0) 2173 – 39 26 999 / Internet: www.borchers.com / E-Mail: info.info@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.