

Water thinnable red two-pack PU topcoat, based on Bayhydrol A 145 / Bayhydur 304

Component 1

Raw Material	Supplier	% by wt.
Bayhydrol A 145	(1)	93.6
Borchi® Gen 0851	(2)	2.1
Borchi® Gel PW 25	(2)	0.3
Surfynol 104 BC	(3)	2.0
Irgazin® Red L 3660 HD	(4)	2.0
<i>Total</i>		<i>100.0</i>
<i>Dispersion: 60 min, on Skandex BAS-20 in 250 ml screw-top jar with 200 g Zr-Silicate grinding beads</i>		

Component 2

Bayhydur 304	(1)	27.7
Dipropylene glycol dimethyl ether	(5)	4.8
<i>Total</i>		<i>32.5</i>
<i>Incorporation: stir for approx. 5 min in a dissolver</i>		

Application

Compressed-air spraying

Data

NCO : OH - ratio	1.5 : 1
Ratio Comp. 1 : 2	3.1 : 1
Thinning with water	approx. 15 %
Spray viscosity, DIN 53211-cup 4mm, at 23 °C	approx. 30 s
Pot life	approx. 2 h
Drying	dust free tack free approx. 30 min approx. 3 h
Haze and Gloss (20° angle), DIN 67530 / ISO 2813	20 / 86

Suppliers

- (1) Covestro (www.covestro.com)
- (2) Borchers (www.borchers.com)
- (3) Air Products (www.airproducts.com)
- (4) BASF (www.basf.com)
- (5) Clariant (www.clariant.com)

Updated: 15.04.2020

Borchers GmbH

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666
Fax: +49 (0) 2173 – 39 26 999 / Internet: www.borchers.com / E-Mail: info.info@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.