

Aqueous white glossy two-pack PU topcoat, with high chemical resistance, based on Bayhydrol A XP 2695 and Bayhydur 304 / XP 2759

	Raw Material	Supplier	% by wt
Comp. 1	1. Bayhydrol A XP 2695, 41% in water / butoxy propanol	(1)	44.63
	2. Dimethylethanolamin, 10% in water	(2)	2.40
	3. Surfynol 104 BC, 50% in butyl glycol	(3)	0.58
	4. Borchi® Gel 0621	(4)	0.15
	5. Borchi® Gol LA 200 , 10% in butyl glycol	(4)	0.74
	6. Borchi® Gen 0851	(4)	0,95
	7. Sachtleben R-KB-4	(5)	23.44
	8. Water		1.18
	<i>Total</i>		<i>74.07</i>
Comp. 2	9. Bayhydur 304, 100%	(1)	4.61
	10. Bayhydur XP 2759, 70% in methoxy propyl acetate	(1)	18.46
	11. Methoxy propyl acetate		2.86
	<i>Total</i>		<i>100.00</i>

Production indications ***Formulation Topcoat Comp. 1***
 Place const.1. in a vessel. Stir in successively const. 2.-6. (5 min at 2000 rpm). Add gradually const.7. under stirring at approx. 2000 rpm. Then pre-disperse for 10 min at approx. 2000 rpm and further disperse for 60 min in the mill base (T ≤ 30°C) until reaching particle size ≤10µm. Add gradually const.8. under stirring. Afterwards filtrate.
Leave to deaerate for one day.

Formulation Hardner Comp. 2
 Mix Bayhydur 304 and Bayhydur VP LS 2759 in ratio 1:4.
 Add methoxy propyl acetate and homogenize.

Mix Comp. 1 and Comp. 2 and homogenize, then add approx.25% water for adjusting the spray viscosity.

Application Spraying using HVLP-pneumatic flow cup spray gun (nozzle 1.4mm /air pressure: approx. 1.9 bar)

Technical data

NCO : OH - ratio	1.5 : 1
Mixing ratio (comp. 1 : comp. 2)	10 : 4
Pigment : Binder - ratio	0.7 : 1
Spray viscosity, DIN 53211-cup 4 mm, at 23 °C	approx. 20 s
VOC (calculated acc. Directive 1999/13/EC)	approx. 186 g/l
Solid content on application	approx. 50 %
Drying time (DIN 53150; TG 1 / TG 3)	0,5 h / 1 h
Gloss 20° / 60° / Haze (DIN EN ISO 2813)	82 / 90 / 19
Film Hardness (pendulum hardness tester-König; DIN EN ISO 1522)	after 1 d / 23 °C after 14 d / 23 °C
	130 s 175 s

Suppliers

- (1) Covestro (www.covestro.com)
- (2) Riedel de Haen (www.riedeldehaen.de)
- (3) Air Products (www.airproducts.com)
- (4) Borchers (www.borchers.com)
- (5) Venator (www.venatorcorp.com)

Updated: 16.04.2020

Borchers GmbH

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666
Fax: +49 (0) 2173 – 39 26 999 / Internet: www.borchers.com / E-Mail: info.info@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.