

Aqueous white glossy two-pack PU topcoat, fast drying, good hardness, based on Bayhydrol A 2470 / Bayhydur 304

	Raw Material	Supplier	% by wt.
Comp. 1	1. Bayhydrol A 2470, 45% in water / solvents mixture	(1)	42.60
	2. Surfynol 104 BC	(2)	0.70
	3. Borchi® Gel Thix 921	(3)	0.14
	4. Borchi® Gol LA 200 , 10% in butyl glycol	(3)	0.88
	5. Borchi® Gol LA 50	(3)	0.30
	6. Borchi® Gen SN 95	(3)	2.24
	7. Sachtleben R-KB-4	(4)	28.04
	8. Water		5.59
	<i>Total</i>		<i>80.49</i>
Comp. 2	9. Bayhydur 304, 100%	(1)	15.61
	10. Butoxyl		3.90
	<i>Total</i>		<i>100.00</i>
Production indications			<i>00</i>
			<i>for</i>
			<i>dd</i>

Application

Spraying using HVLP-pneumatic flow cup spray gun (nozzle 1.4mm /air pressure: approx. 1.9 bar)

(Before application add approx. 20% water for adjusting the spray viscosity.)

Technical data

NCO : OH - ratio	1.5 : 1
Mixing ratio (comp. 1 : comp. 2)	100 : 24
Pigment : Binder - ratio	0.8 : 1
Spray viscosity, DIN 53211-cup 4 mm, at 23 °C	approx. 20 s
VOC (calculated acc. Directive 1999/13/EC)	approx. 165 g/l
Solid content on application	approx. 57 %
Drying time (DIN 53150; TG 1 / TG 3)	0,5 h / 2 h
Gloss 20° / 60° / Haze (DIN EN ISO 2813; on steel)	80 / 89 / 22
Film Hardness (pendulum hardness tester-König; DIN EN ISO 1522)	after 1 day at 23 °C after 7 days at 23 °C
	115 s 160 s

Suppliers

- (1) Covestro (www.covestro.com)
- (2) Air Products (www.airproducts.com)
- (3) Borchers (www.borchers.com)
- (4) Venator (www.venatorcorp.com)

Updated: 16.04.2020

Borchers GmbH

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666
Fax: +49 (0) 2173 – 39 26 999 / Internet: www.borchers.com / E-Mail: info.info@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.