

Water thinnable white two-pack PU topcoat, based on Bayhydrol A 145 and Bayhydur 304

	Raw Material	Supplier	% by wt.
Component 1	1. Bayhydrol A 145, 45%	(1)	34.56
	2. Surfynol 104 E	(2)	0.79
	3. Sachtleben R-KB-4	(4)	29.35
	4. Water		6.00
	5. Bayhydrol A 145, 45%	(1)	13.88
	6. Borchi® Gel THIX 921	(3)	0.15
	7. Borchi® Gol LA 50	(3)	0.16
	8. Borchi® Gol LA 200	(3)	0.31
	<i>Total</i>		<i>85.20</i>
<i>Place const. 1. Add under mixing const. 2.-4.; 10 min. at 2000 rpm pre-dispersion, then dispersion for 60 min in bead mill. Add under mixing const. 5.-8. Mix for further 30 min. at 2000 rpm. Let rest 1 day for deaeration.</i>			
Component 2	9. Bayhydur 304	(1)	14.80
	<i>Total</i>		<i>100.00</i>
	Water (for thinning)*		20.00
<i>Incorporation: stir for approx. 10 min in a dissolver</i>			

* to adjust the spray viscosity

Data

NCO : OH - ratio	1.5 : 1
Spray viscosity, DIN 53211-cup 4mm, at 23 °C	approx. 34 s
Pendulum hardness, König method - DIN EN ISO 1522 (100 µm wet film thickness on glass) after: 1 day / 3 days / 7 days	62 / 102 / 115
Haze and Gloss (20°/60°angle), DIN 67530 / ISO2813	20 / 76 / 84

Suppliers

- (1) Covestro (www.covestro.com)
- (2) Air Products (www.airproducts.com)
- (3) Borchers (www.borchers.com)
- (4) Venator (www.venatorcorp.com)

Updated: 16.04.2020

Borchers GmbH

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666
Fax: +49 (0) 2173 – 39 26 999 / Internet: www.borchers.com / E-Mail: info.info@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.