

High glossy white two-pack PU topcoat,  
based on Desmophen 1300 / Desmodur L 75

	Raw Material	Supplier	% by wt.
<b>Component 1</b>	Desmophen 1300, 75% in xylene	(1)	48.4
	<b>Borchi® Gen 0451</b>	(2)	2.0
	Sachtleben R-KB-6	(3)	32.0
	Aerosil R 972	(4)	0.3
	Bentone SD 2	(5)	0.4
	<b>Borchi® Gol LA 200</b> , 10% in butyl acetate	(2)	1.0
	<i>Dispersion: 30 min. under cooling at 2500 rpm</i>		
<b>Let down</b>	Butyl acetate		3.2
	Ethyl acetate		2.9
	Methoxy propyl acetate		1.9
	<b>Borchi® Gol OL 17</b> , 10% in butyl acetate	(2)	2.0
	CAB 531.1, 10% in butyl acetate	(6)	4.9
	<b>Borchi® Gol LA 200</b> , 10% in butyl acetate	(2)	1.0
	<i>Sum: Comp. 1</i>		100.0
<b>Component 2</b>	Desmodur L 75	(1)	29.4
	Butyl acetate		38.3
	<i>Sum: Comp. 1 +2</i>		167.7

<b>Data</b>		
NCO : OH - ratio		1 : 1
Solids content Comp. 1		ap. 71.3 %
Binder content Comp. 1		ap. 36.3 %
Pigment content Comp. 1		ap. 32 %
Viscosity Comp. 1, DIN 53211-cup 4 mm, at 23 °C		82 s
Spray viscosity, DIN 53211-cup 4 mm, at 23 °C		15 s
Pot life		ap. 6 h
Drying (tack free at room temperature)		ap. 3 h
Hardness, (König method) DIN EN ISO 1522 - after 1 week		172 s
Gloss (20°/ 60°angle), DIN 67530 / ISO 2813		90 / 99

## Suppliers

- (1) Covestro ([www.covestro.com](http://www.covestro.com))
- (2) Borchers ([www.borchers.com](http://www.borchers.com))
- (3) Venator ([www.venatorcorp.com](http://www.venatorcorp.com))
- (4) Evonik ([www.aerosil.com](http://www.aerosil.com))
- (5) Elementis ([www.elementis.com](http://www.elementis.com))
- (6) Eastman Chemical ([www.eastman.com](http://www.eastman.com))

Updated: 17.04.2020

---

**Borchers GmbH**  
Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666  
Fax: +49 (0) 2173 – 39 26 999 / Internet: [www.borchers.com](http://www.borchers.com) / E-Mail: [info.info@borchers.com](mailto:info.info@borchers.com)

---

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

---