

Solventborne pigment concentrates, binder free

Pigment paste	A	B	C	D
<i>Colour index</i>	<i>P.V. 19</i>	<i>P. R. 254</i>	<i>P.Y. 213</i>	<i>P.O. 36</i>
Pigment Trade name	Hostaperm ER 02 (1)	Irgazin® Red L 3660 DPP (1)	Hostaperm gelb H5G (1)	Sunfast orange 36 (2)
Pigment	20.0	20.0	20.0	20.0
Borchi® Gen 0451 (3)	4.0	1.7	4.0	6.0
Methoxy propyl acetate	76.0	78.0	76.0	73.7
Aerosil 200 (4)	—	0.3	—	0.3
<i>Total</i>	<i>100.0</i>	<i>100.0</i>	<i>100.0</i>	<i>100.0</i>
Dosage of additive active content based on pigment content	20 %	8.5 %	20 %	30 %

All indications are as supply form (in % by wt).

Dispersion: 60 min, on Skandex BAS-20, with 150 g Zr-Silicate grinding beads (2mm)

Data		
Particle size (using Grindometer):		< 10 µm
Consistency:		free-flowing
Viscosity (at shear rate 100 s ⁻¹ ; 23 °C):		< 350 mPa·s
Storage (2 weeks at 50 °C):		stable (no significant alteration of the viscosity and particle size)

- Suppliers**
- (1) Clariant (www.clariant.com)
 - (2) Sun Chemical (www.sunchemical.com)
 - (3) Borchers (www.borchers.com)
 - (4) Evonik (www.aerosil.com)

Updated: 17.04.2020

Borchers GmbH

Berghausener Str. 100 / 40764 Langenfeld / Telephone: +49 (0) 2173 – 39 26 666
 Fax: +49 (0) 2173 – 39 26 999 / Internet: www.borchers.com / E-Mail: info.info@borchers.com

Our product information is given in good faith but without warranty. This also applies where proprietary rights of third parties are involved. This information does not release the customer from the obligation to test our products as to their suitability for the intended processes and uses. The application, use and

processing of our products and the products manufactured by the customer on the basis of our technical advice are beyond our control and, therefore, entirely the customer's own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.