

Anticorrosive coatings

EU SF 2.3.

Corrosion resistant water thinnable paint,
based on Resydrol AZ 436w/45 WA, VOC ≤ 150g/l

Formulation	Raw Material	Supplier	% by
1.	Resydrol AZ 436w/45 WA	(1)	56,9
2.	Ammoniak, 10%ig		1,0
3.	Wasser		13,2
4.	Borchi® Gel 0626	(2)	3,0
5.	Surfynol SE-F	(3)	0,3
6.	Borchers® AF 1171	(2)	0,3
7.	Heucophos ZCPP	(4)	4,7
8.	Bayoxide® Z active	(2)	0,5
9.	Micro Talc AT extra	(5)	8,0
10.	Millicarb	(5)	5,2
11.	Bayferrox 130M	(6)	6,3
Pos. 1.-12. 30 min in der Perlmühle dispergieren.			
12.	Borchi® OXY Coat 1101	(2)	0,15
13.	Ascinin® Anti Skin 0445	(2)	0,15
14.	AMP 90	(7)	0,3
Pos. 12. - 14. zugeben und 15 min. bei 500 U/min. rühren.			
Total			100,0

Technical Data

pH-value	8.5 - 9.3 (DIN 53875) evtl. adjust with	8.9
Viscosity Brookfield	Spindel 6/20 rpm; 20 °C	8500mPas
Viscosity Krebs-Stormer	200 rpm; 20 °C	115 KU
Pigment Volume Concentration		11.7 %
Density	20 °C	1.26g/cm ³
Solids-content	1.5 h at 125 °C	approx. 54 %
Drying	DIN 53150	TG1 - 15min. TG3 - 45min.
VOC-content (on	DIN EN ISO 11890-1	approx. 150 g/l
Cross-cuttest	DIN 52151 (after 1 week)	0 / 0

Suppliers

- (1) Cytec Surface Specialties (www.cytec.com)
- (2) Borchers (www.borchers.com)
- (3) Air Products (www.airproducts.com)
- (4) Heubach (www.heubachinternational.de)
- (5) Mondo Minerals (www.mondominerals.com)
- (6) Lanxess (www.lanxess.com)
- (7) Angus Chemical (www.angus.com)

Berghausener Str. 100 / 40764 Langenfeld / Telephone: + 49 (0) 2173 - 39 26 666 Fax: +49 (0) 2173 - 39 26 999 / Internet:
www.borchers.com / E-Mail: info.info@borchers.com

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.