

Borchi® Boost Testing Plan

Phase 1:

1. Add each Borchi® Boost product into the incompatible system individually
 - a. Below is a table of test formulations
 - i. Formulations are out of 100 for ease of calculation, but you can scale to whatever is appropriate for your equipment
 - ii. Borchi® Boost 510W is used at 2% as it is 50% active in water, the other two additives are 100% active
2. Mix/Agitate for 1 minute at 1500 rpm
3. Drawdown the sample next to a control sample
4. Perform a rubout test to see if the Boost produces a homogenous coating with reduced/no rubout

Materials	Control	Sample 1	Sample 2	Sample 3
Incompatible Base	100.00	100.00	100.00	100.00
Borchi® Boost 510W	0.00	2.00	0.00	0.00
Borchi® Boost 540WS	0.00	0.00	1.00	0.00
Borchi® Boost 570WS	0.00	0.00	0.00	1.00
Total	100.00	102.00	101.00	101.00

Phase 2:

1. Add the best Borchi® Boost product from Phase 1 into the incompatible system as a ladder at 1%, 2%, and 3%
 - a. Below is a table of test formulations
 - i. If Borchi® Boost 510W performs the best, the samples would be 2.00, 4.00, 6.00
2. Mix/Agitate for 1 minute at 1500 rpm
3. Drawdown the sample next to a control sample
4. Perform a rubout test to see which level of Boost produces the best coating with reduced/no rubout

Materials	Control	Sample 4	Sample 5	Sample 6
Incompatible Base	100.00	100.00	100.00	100.00
Best Borchi® Boost	0.00	1.00	2.00	3.00
Total	100.00	101.00	102.00	103.00

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet: www.borchers.com / E-Mail: info.us@borchers.com

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing