

## Borchers® Deca 161

Combination drier for oxidatively drying alkyd resins

### Physical Characteristics

Appearance	Clear, violet liquid
Metal content	Ca: 4.90 - 5.10 % Co: 1.60 - 1.75 % Zr: 4.90 - 5.10 % DIN 55901 Total: 11.40 - 11.95 % (calculated)
Non-volatile content	62.00 - 74.00 % ISO 3251 (2g, 3h, 105 °C)
Viscosity	Max. 500 mPa·s ISO 3219 (A) (20°C)
Specific gravity	NA
Density	1.010 - 1.050 g/cm <sup>3</sup> DIN 51757 (20 °C)
Solvent	White-spirit containing <1 % aromatics

### Features

- Developed for use in solvent-based systems that dry by oxidation
- Ensures uniform drying of the paint film
- The primary drier yields optimum surface drying
- Improves hardness

### Applications

- Solvent-based systems based on medium- and long-oil alkyds that dry by oxidation

### Dosage

Application trials have shown the addition of Borchers® Deca 161 to be between 2.5 and 5.0 %, calculated on resin solid and depending on the binder and pigments used in the formulation.

### Storage

Protect from the effects of weathering and store at temperatures below 50 °C. Once opened, containers should be resealed immediately after each removal of the product.

### Safety

Please refer to our safety data sheet for information relating to product safety.

---

811 Sharon Drive / Westlake, OH 44145 / Telephone: +1 800-321-9696 / 440-899-2950 / Fax: +1 440-808-7114 / Internet:  
www.borchers.com / E-Mail: borchersinfo@milliken.com

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at [www.milliken.com/terms](http://www.milliken.com/terms) (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.