

Wood & Furniture Coatings

EU SF 3.21.

High glossy white two-pack PU topcoat, based on Desmophen 1300 / Desmodur L 75

Com	pone	nt 1
-----	------	------

Supplier	% by wt.
(1)	48.4
(2)	2.0
(3)	32.0
(4)	0.3
(5)	0.4
(2)	1.0
_	<u>3.2</u>
	2.9
	1.9
(2)	2.0
(6)	4.9
(2)	1.0
	100.0
	(1) (2) (3) (4) (5) (2) (2)

Let down

Component 2

Desmodur L 75	(1)	29.4
Butyl acetate		38.3
Sum: Comp.1+2		167.7

Data

NCO: OH - ratio	1:1
Solids content Comp.1	ap. 71.3 %
Binder content Comp.1	ap. 36.3 %
Pigment content Comp.1	ap. 32 %
Viscosity Comp.1, DIN 53211-cup 4 mm, at 23 °C	82 s
Spray viscosity, DIN 53211-cup 4 mm, at 23 °C	15 s
Pot life	ap. 6 h
Drying (tack free at room temperature)	ap. 3 h
Hardness, (König method) DIN EN ISO 1522 - after 1	172 s
Gloss (20° / 60° angle), DIN 67530 / ISO 2813	90/99



Suppliers

- (1) Covestro (www.covestro.com)
- (2) Milliken (www.milliken.com)
- (3) Venator (www.venatorcorp.com)
- (4) Evonik (www.aerosil.com)
- (5) Elementis (www.elementis.com)
- (6) Eastman Chemical (www.eastman.com)

borchers.com/contact

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

Edition: 12/2023

Milliken